

Technical Data Sheet

URAGARD

HT 100

DESCRIPTION

Uragard HT 100 is a fast-curing, heavy-duty, polyurethane flooring system with built-in flexibility, making it particularly useful for freezer or cold room environments. Uragard HT 100 ensures a durable, impact and wear resistant surface at operating temperatures from -5 to -35 degrees centigrade.

KEY BENEFITS

- Suitable for freezers / cold rooms
- Anti-slip surface
- Fast curing, single application
- Excellent chemical resistance
- Excellent impact and wear resistance at -5 to -35°C
- Temperature resistant from 50°C to -35°C
- Optional biocide additive

TECHNICAL DATA

John Lord is an ISO 9001:2000 accredited company and all John Lord products are manufactured strictly to ISO quality standards.

Performance Data (at temp range -5 to -35°C)

Compressive Strength:	53.0 N /mm ²
Flexural Strength:	13.0 N /mm ²
Tensile Strength:	5.0 N /mm ²
Temperature Resistance:	Constant -35°C to 50°C.
Flash Steam Cleanable:	No
Slip Resistance	Safe Surface in Dry and Wet Conditions
Water Permeability	Nil

Actual performance may vary from the above values depending on site conditions.

Physical Properties

Complies with BS 8204-6 / FeRFA Type 6

System Make-Up:

Primer (s)	1x coat Uragard Primer
System	1x application Uragard HT 100
Sealer Coat (s)	None
Optional Variations	Biocide additive

System Details:

Finish:	Resin rich anti-slip
Thickness:	9-12 mm
Standard Colours:	Red, Buff, Terracotta, Green, Dark Grey

Chemical Resistance

Resistant to a wide range of chemicals. For full details consult John Lord Technical Dept.

Curing Time

Floor can go into service after the following minimum cure periods at 18°C and above:

Light traffic:	24 hours
Heavy traffic:	48 hours

Nb. Uragard HT 100 must be allowed to cure fully for 7 days prior to exposing system to operating temperature below 0°C

Shelf Life / Storage

The product should be kept in its original unopened container until use.

The product should be stored in weather tight conditions, at temperatures between 10°C and 25°C, avoiding direct sunlight. Under these conditions this product has a shelf life of up to 6 months.

In-Service Maintenance

Good housekeeping and regular cleaning can considerably extend the service life of a floor, will enhance the floor's appearance and reduce soiling tendencies.

Suitable cleaning methods for this product include:

- Rotary scrubbing machine and /or warm water washing (up to 60°C) with suitable detergent products – see John Lord Cleaning Guide for further details

APPLICATION INFORMATION

John Lord recommend that all products are installed by their own Contracts Department. John Lord Contracts Department provide a professional service with experienced Project Management supervision and skilled, trained and NVQ /CSCS approved applicators.

Suitable Applications

- Freezer / Chiller / Cold Room Environments

Substrate Requirements

Concrete substrates should be a minimum strength of 35N/Sq.mm, with a minimum cement content of 320 –350kgs per cubic metre. Substrates should have minimum laitance and be free from dust and contamination. Substrates should be free of any unseen defects such as structural instability or intermediate delamination. Tolerances and levels in concrete substrates should be of the standard required of the seamless resin finish. Substrates should be dry to 75% RH as per BS8204 or by Vaisala thermo hygrometer type HMI 31. Substrates should incorporate an effective D.P.M and be free from rising dampness, moisture and osmosis. Newly laid substrates must be allowed sufficient 'drying out' time prior to overlaying. The drying time required will depend upon ambient temperatures, humidity and substrate thickness. Uragard HT products should NOT be applied to the following substrates: *Asphalt, Unmodified sand cement screeds, PVC tiles or sheet.*

Substrate Preparation

Careful preparation of the substrate is essential. A detailed inspection of the substrate must be undertaken to determine the nature of preparation required eg. mechanical scarifying, shot blasting, diamond grinding, chemical decontamination, hot compressed air treatment. Steel decking should be prepared to S.A 2.5 or similar. For specialist advice on substrate preparation, contact John Lord.

Application Technique

Temperature: Correct temperature is critical to the successful application of Uragard HT 100 and air temperatures should be maintained between 10°C and 25°C during the application and curing period of this product. We also strongly recommend that the application area is heated to temperatures of between 10°C and 25°C for up to 24 hours prior to application to allow the ambient and substrate temperatures to regulate before the application commences. Materials should also be kept in a warm area of 12°C minimum temperature for 12 hours prior to application.

Statement of Responsibility

The technical data and application information within this John Lord Technical Data Sheet is provided as an introduction to the system only and may vary according to on-site or environmental conditions. As the information provided is of a general nature, no guarantee is implied and it is the responsibility of the client or user to discuss in detail with John L. Lord & Son, the suitability of the product for a particular application or requirement beforehand. John L. Lord & Son cannot accept any responsibility of work and the subsequent performance of their systems that are not controlled by their own contracting services.

John L. Lord & Son reserve the right to alter information contained in this document without prior notification, and it is the responsibility of the client or user to obtain the most recent issue.

De-humidifiers must be used where high humidity conditions prevail. Ensure adequate ventilation during application.

Priming: The dry, prepared, dust-free substrate should receive a roller applied tack coat of Uragard primer. After approximately one hour tack off time, the Uragard HT 100 can be applied.

System: The Uragard HT 100 should be mixed and trowel applied to a thickness of between 9-12 mm.

Joints: All known expansion joints should be followed through the resin floor finish using Epiflex jointing mastic. If concrete movement or cracking takes place after application then reflective cracking of the topping may occur.

Note:

The texture of the above product may on the finished floor surface provide a banded or slightly variable appearance. This is a natural, visual aspect of the system, which can also be influenced by atmospheric conditions and is not defective in anyway. Polyurethane systems have limited colour stability which can result in discoloration of the floor over a period of time upon exposure to U.V light. Our standard colour range has been carefully chosen to provide a colour range limiting the extent of discolouration.

Precautions

Appropriate PPE such as gloves, goggles and barrier cream should be worn during mixing and application of this product. Product should not come into contact with the skin or eyes, or be swallowed. Avoid inhalation.

For full health and safety hazard information, please refer to the John Lord Safety Data Sheet (SDS) for each component of this product. COSHH and SDS documents can be obtained from our Bury Office or via our website www.john-lord.co.uk.

